



Vapour Seal Mastic 2-16

| | |
|------------------------------|---|
| Colour | Black |
| Consistency | Soft paste |
| Specific Gravity | 1.02kgs/litre |
| Average Non-Volatile Content | 60% by weight |
| Coverage | Track coat: 0.80mtrs ² /litre (1.2mm wet film thickness) Finish coat: as per track coat |
| Bonding/Drying Time | 24 hours (under favourable conditions) |
| Application | Trowel or Spray |
| Clean-up | Wet: Water, Dry: White Spirit |
| Service Temperature Limits | -30°C to +80°C |
| Flammability | Wet: Non flammable, Dry: Burns |
| Water Vapour Transmission | 0.05 perm at 1.00mm dry film thickness |
| Shelf Life | 12 months minimum (unopened container) |

Description

Vapour Seal Mastic 2-16 is a rubber bitumen emulsion for trowel or spray applications. Designed to provide a vapour seal to the walls, ceilings and floors of cold stores prior to insulating. All surfaces should be smooth, sound and dry. Surfaces which are dusty must be primed with Primer 3-24 applied by brush or spray at 3.70 mtrs²/litre.

NB Suitable for Expanded Polystyrene.

Method of Use

Apply two coats of Mastic 2-16 to the recommended wet film thickness and by the desired method. Allow 24 hours between coats under favourable drying conditions. Should reinforcement be required, use a layer of W10 open weave glass cloth embedded into the first coat, allow overlaps of at least 50mm.

Important

Stir well before use. Apply to clean, dry and dust free surfaces. Protect from freezing during storage. Store between 5 degs C and 30 degs C. Do not apply if the temperature is likely to fall below 5 degs C before coating is fully cured. Avoid contact of wet mastic with skin, eyes and clothing. Vapour Seal Mastic 2-16 should be allowed to dry thoroughly before any adhesive is applied to stick the insulation.

Sealumet (Australia) Pty Limited

Mailing Address : PO Box 2218, Warwick, Perth, WA, 6024

Warehouse : Unit 2, 6 Langar Way, Landsdale, Perth, WA - 6065

Telephone : +618 6201 6153, Fax : +618 9303 4560

E-mail: enquiries@sealumet.com Website: www.sealumet.com

DISCLAIMER

These data sheets are based on specifications, data and test results at time of publication. No guarantee as to completeness, accuracy or results is either expressed or implied. The suitability for an intended use is the responsibility of the user. As choice of material, method of application and site conditions are beyond our control we accept no liability for direct or consequential damages. Any material proved to be defective within the published shelf life* will be replaced. *From date of supply.